



96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Received:08/04/2016	Completed:08/05/2016	Letter: U	BG	P.O.#:	Test Report #:	3-14668-0-
---------------------	----------------------	-----------	----	--------	----------------	------------

Client's Identification Style: Anzio. Composition: 100% Polyester. Weight: 220 g/m². Thickness: 0.4mm. End Use: Interior Roller Shades.

Tested For: Jessica Bondell **Key Test: CA 1237 Sm** 195
 Rollease Acmeda, Inc.
 200 Harvard Avenue
 Stamford, CT 06902 **Tel: 1-(203)-964-1573** **Ext:**
Fax: 1-()- -

LE: 1993; V 09/15 NTR 04/16 PC: 1H /jd SM/mg

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - INTERIOR MATERIALS QUALIFICATION


RESULTS REPORTED: Initially
 After 3 dry cleanings
 After 5 launderings @ 160°F

RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)
Warp:	1	0	0	4.2
	2	0	0	3.5
	3	0	0	3.5
	4	0	0	4.2
	5	0	0	3.4
	Avg:	0		
Fill:	6	0	0	3.0
	7	0	0	3.0
	8	0	0	3.3
	9	0	0	3.8
	10	0	0	4.5
	Avg:	0		

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 6.8 oz/yd²

ACCEPTANCE CRITERIA:
 Afterflame: 4.0 seconds maximum average for warp or fill
 Afterglow: (see Note #2 below)
 Char Length: 6.0 inches maximum for any individual specimen

- NOTES:
1. An asterisk (*) next to any char length measurement indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd².
 2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria.



96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Received:08/04/2016	Completed:08/05/2016	Letter: U	BG	P.O.#:	Test Report #:	3-14668-0-
Client's Identification	Style: Anzio. Composition: 100% Polyester. Weight: 220 g/m ² . Thickness: 0.4mm. End Use: Interior Roller Shades.					
Tested For: Jessica Bondell Rollese Acmeda, Inc. 200 Harvard Avenue Stamford, CT 06902	Key Test: CA 1237 Sm				195	
	Tel: 1-(203)-964-1573		Ext: .			
	Fax: 1-()- -					
<p>CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:</p> <p>[x] Complies; [] Does not comply</p> <p>REMARKS: None.</p> <p>NOTE: The number of test specimens and Acceptance Criteria are based on a proposed revision issued and implemented by the California State Fire Marshal in August 1993. In substance, the following has occurred:</p> <ol style="list-style-type: none"> 1. A maximum afterflame of 4 seconds is permitted as opposed to 1 second. 2. It was clarified that the char length maximum of 6 inches applies to any individual specimen and is not an average requirement. 3. Ten specimens are tested in lieu of 6 specimens. <p>This report issues the conclusion to Section 1237 based on the California State Fire Marshal's continued endorsement of the proposed revision.</p> <p>CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.</p> <p>----- AUTHORIZED SIGNATURE GOVMARK /pm /mo</p> <p style="text-align: right;"><i>Robert I. Brown</i></p> <p style="text-align: center;">(Page 2 of 2)</p> <p style="text-align: right;">AUG 08 2016</p>						

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from Govmark.

File Copy